

	L #	Hits	Search Text	DBs
1	L1	178083	glass adj (fiber filament strand)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
2	L2	38745	1 and epoxy	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
3	L3	4512	2 and epichlorohydrin	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
4	L4	3329	3 and bisphenol	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
5	L5	2517	4 and coat\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
6	L6	93	5 and (epoxy adj resin adj hardener)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
7	L7	76	6 and liquid	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
8	L8	63	7 and reaction	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
9	L9	63	8 and glass	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
1	L1	8	chem-res	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM TDB
2	L2	3	1 and waterpoxy	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM TDB
3	L3	1	2 and glass	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM TDB
4	L4	2	2 not 3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM TDB
5	L5	97285 3	"8" and glass	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM TDB
6	L6	4	1 and glass	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM TDB
7	L7	12	waterpoxy and glass	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM TDB